


# Development of SOFC Stack Components for Operation at 600°C

## European Integrated Project SOFC600

Bert Rietveld


Energy Research centre of the Netherlands (ECN)

Frans van Berkel en Ye Zhang-Steenwinkel (ECN, NL),  
Etienne Bouyer (CEA, F), John Irvine (University St. Andrews, UK),  
Mohan Menon (Risø-DTU, DK), Leszek Niewolak and Sonja Gross (FZJ, D), Andre  
Heel and Peter Holtappels (EMPA, CH), Stefano Modena (HTceramix, CH)



## Project data

- FW6 Integrated Project SES6-2006-020089
- Duration 1<sup>st</sup> March 2006 – 28 February 2010
- 21 participants
  
- Research and development project with emphasis on development of novel materials, (near-nano) microstructures and manufacturing processes
- Relatively high level of basic R&D, less application targeted (generic)



# EU SOFC600 Project Consortium

## 7 Universities

- Basic research

## 11 R&D organisations


- Basic research + development

## 3 Industrial companies, all SMEs

- Development + implementation


ECN	Netherlands
HTceramix	Switzerland
CEA	France
EMPA	Switzerland
FZJ	Germany
Imperial College	United Kingdom

Uni Karlsruhe	Germany
Uni St.Andrews	United Kingdom
Uni Oxford	United Kingdom
Uni Leoben	Austria
CNRS Bordeaux	France
TOFC	Denmark
AECA (NTDA-SOFC)	Spain
NRC	Canada
DICP	China
IPMS	Ukraine
SJTU	China
BIC	Russia
PMI	Belarus
VTT	Finland
DTU	Denmark




## Project objectives and scope

- Specification of stack components for operation at 600°C aiming for endurance and cost
  - Anodes, cathodes and electrolytes
  - Interconnect materials
  - Contact and barrier/protective coatings
  - Seals
- Components are demonstrated by integration in the current cell and stack technology of the developers
- The development and delivery of full cells and stacks itself is outside the scope of the project
- Non technical objectives (WP6)
  - Dissemination and communication project achievements
  - Project website
  - Workshops (internal and external)
  - Initiate and contribute to European HFP-SOFCnet




## Motivation for Low Temperature SOFC

- Lifetime/degradation
  - Reduced degradation rate of thermally activated cell degradation mechanisms
  - Reduced corrosion rate of preferably cheap steels for interconnects
  - Metal, metal-ceramic (compressible) seals and non crystallizing glass
  - Stability of contact coatings
  - Lower sensitivity for combined thermal-redox cycles
- Costs
  - Lifetime
  - Cheap interconnect steels and BOP materials
  - Industrial, cost effective manufacturing processes
- Fuel flexibility and high efficiency
  - H<sub>2</sub> and reformates
  - Internal reforming of NG (simplest and most efficient system)
    - Low catalytic activity for C deposition



## Project targets

- SOFC cell at 600°C
  - Area Specific Resistance (ASR) below 0,5  $\Omega\cdot\text{cm}^2$
  - Degradation rate below 1.5  $\text{m}\Omega\cdot\text{cm}^2\cdot\text{hr}^{-1}$  (0.05 %V.khr<sup>-1</sup>)
  - For ISR at S/C = 2: 0.8  $\Omega\cdot\text{cm}^2$  and 3  $\text{m}\Omega\cdot\text{cm}^2\cdot\text{hr}^{-1}$
  - Robustness: 5 ppm S, 100 redox cycles, internal reforming capability, reduced coke formation activity
- Single repeating unit (cell + coatings + interconnect)
  - ASR below 0.7  $\Omega\cdot\text{cm}^2$
  - Degradation rate below 3  $\text{m}\Omega\cdot\text{cm}^2\cdot\text{hr}^{-1}$
  - For ISR at S/C = 2: 1.0  $\Omega\cdot\text{cm}^2$  and 5  $\text{m}\Omega\cdot\text{cm}^2\cdot\text{hr}^{-1}$
- Gas tightness seals
  - External leakage below 0.5% of fuel/oxidant flow at  $\Delta P = 20$  mbar
  - Internal leakage below 0.5% at  $\Delta P = 20$  mbar
- Main precondition: projected stack costs < 2500 Euro/kW<sub>e</sub>
  - Developments based on cost-effective materials and manufacturing




## Phases and time schedule


- Evaluation State-of-the-Art components
  - Identification of most critical components
  - Reference for monitoring progress
- Basic components
  - 'Easy' fuels like H<sub>2</sub> and reformat
  - Focus is performance and endurance; sub-focus thermal and redox cycling
- Advanced components
  - Components for internal reforming of natural gas
  - Focus is reforming catalysis; sub-focus S tolerance and low catalytic activity for C deposition

1. Evaluation SoA


2. Basic components for 600°C, H<sub>2</sub> and NG reformat


3. Internal reforming






## Project flow sheet and go / no-go






## Cell development lines


- High(est) performance and endurance at stationary operating conditions
  - Large scale stationary systems
  - ASC: Ni based anode – SZ electrolyte – Sr containing cathodes
- High robustness cell
  - Redox, Sulphur and Chromium tolerance, reduced C depostion
  - For cycling and off-spec operating conditions
  - Small scale stationary & transport applications
  - ASC: titanate anode – SZ electrolyte – nickelate cathode
  - ESC: Ni based anode – 10Sc1CeSZ electrolyte – nickelate cathode
- Performance and robustness evaluated/demonstrated with
  - H<sub>2</sub> (reformate)
  - Internal Steam Reforming of NG







## Main Achievements - High Performance Cell


T 600°C, Fuel 60 H<sub>2</sub> – 40 H<sub>2</sub>O






## Cell optimisations / alternatives







## Performance with ISR operation at 600°C




- Performance target ( $0.8 \Omega \cdot \text{cm}^2$ ) amply met
- Further activities will focus degradation at ISR conditions
  - First short-term results show values similar to  $\text{H}_2$  operation




# Performance and Endurance at ISR operation







## High performance ASC and Endurance

Cell description	ASR at 0.7V and 600°C ( $\Omega \cdot \text{cm}^2$ )	Degradation $\text{m}\Omega \cdot \text{cm}^2/\text{hr}$	Degradation $\text{V}\%/\text{hr}$
ASC(high porosity) - GCO(FZJ_PVD) - LSC	0.25	17.0 ( $\text{H}_2$ )	0.9 ( $\text{H}_2$ )
ASC - GCO(PVD_FZJ) - LSC	0.33	--	--
ASC - GCO(NRC_RSMT) - LSC	0.34	--	--
ASC -1 $\mu\text{m}$ 8YSZ electrolyte - GCO(SP) - LSC	0.41	--	--
ASC(impreg) - 2 $\mu\text{m}$ 8YSZ electrolyte - GCO(SP) - LSC	0.44	--	--
ASC(impreg) - GCO(SP) - LSC	0.47	6.5 ( $\text{H}_2$ )	0.3 ( $\text{H}_2$ )
ASC(impreg, MgO-doped) - GCO(SP) - LSC	0.48	--	--
ASC(mixed, MgO-doped) - GCO (SP) - LSC	0.49	4.9 ( $\text{H}_2$ ) 22.0 ( $\text{CH}_4$ )	0.2 ( $\text{H}_2$ ) 1.0 ( $\text{CH}_4$ )
ASC(SoA-ECN) - GCO(SP) - LSC	0.54	0 ( $\text{H}_2$ )	~0 ( $\text{H}_2$ )





## Combined thermal and redox cycle






## Robust Cell Development (FZJ)



Anode substrate Y-doped  $\text{SrTiO}_3$



Survived 200 redox cycles

Performance at 800°C: 0.94 A/cm<sup>2</sup> at 0.7 V, OCV 1.1 V




# Steel and contact coating


## Typical behaviour of these coatings



- Steels: 1.4509, Crofer22APU, 1.4016, 1.4521, 1.4435, 1.4845, 1.4520
- Contact coatings: LSC, LSCF, LSMC, LNF,  $\text{Pr}_2\text{NiO}_{4+\delta}$




## SRU Performance & Endurance



Targets: ASR 0.7 Ω.cm<sup>2</sup>

ΔASR 3.0 mΩ.cm<sup>2</sup>.khr<sup>-1</sup> equivalent to 0.15 V%/khr







# Seals

Untreated steel


Pre-oxidised




Glas seals that settle at low temperatures



Mica seals cause corrosion of Crofer; pre-oxidation seems to prevent this



Metal + mica seal for HTceramix stack



# Powder manufacturing


## Advantages


- synthesis of nanopowders
  - high temperature & quenching rate (250 000 K/s)
  - one-step synthesis
- no after treatment
- high production rates (400 g.h<sup>-1</sup>)

## Powders manufactured

- Cathode and contact coating materials
  - LSC, LSCF, LNF
  - Pr<sub>2</sub>NiO<sub>4</sub>, NiNd<sub>2</sub>O<sub>4</sub>, NiPr<sub>2</sub>O<sub>4</sub>
- Electrolyte materials
  - Ce<sub>0.036</sub>Y<sub>0.014</sub>Sc<sub>0.648</sub>Zr<sub>3.17</sub>O<sub>7.5</sub>
- Anode materials
  - La<sub>0.7</sub>Sr<sub>0.2</sub>Ti<sub>1.0</sub>O<sub>3</sub>

## Flame Spray Synthesis





## Conclusions

- Cells and cell components
  - Intermediate and final performance targets achieved
  - Degradation targets achieved, but further research required to explain scatter
  - Robust components identified
- Interconnects and coatings
  - Resistivity and corrosion targets met based on 1000 hours tests
- Development low-temperature seal options on schedule
- Powder manufacturing fully operational and fulfilling project needs
- Independent EWGS established
  - Workshop in Sofia on Development needs for SOFC
  - Possible solution for future Luzern SOFC conference created: Swiss AG supported by SOFC stakeholders